

<b>Model No.</b> <b>CK2026</b> <b>(Extra Thick 1.5mm)</b>	<b>High Tenacity Polyester PVC Laminated Fabrics</b>
<b>General Applications:</b>	Construction, Marine (Field) covers, Storage covers and many other applications
<b>Colors:</b>	Pink , Red , Vermilion Orange , Earthy Yellow , Orange , Light Blue , Dark Blue , White , Black , Green , Deep Forest Green , Grey
	粉紅 , 大紅 , 桔紅 , 土黃 , 橙 , 淺藍 , 深藍 , 白 , 黑 , 綠 , 軍綠 , 灰
<b>Type of Products:</b>	



### Physical Properties:

<b>Fabric Detail</b> 網布規格	<b>1000D x 9 x 9</b>			
<b>Item</b> 項目名稱	<b>Test Method</b> 執行標準	<b>Unit</b> 單位	<b>Value</b> 數據	
<b>Thickness</b> 厚度	<b>DIN53353</b>	<b>mm</b>	<b>1.516</b>	
<b>Total Weight</b> 總重量	<b>DIN53352</b>	<b>g/m<sup>2</sup></b>	<b>1826.7</b>	
<b>Tensile Strength</b> 拉伸強度	<b>ISO 1421</b>	<b>N/5cm</b>	經 Warp	<b>1513.7</b>
			緯 Weft	<b>1319.9</b>
<b>Elongation at Break</b> 斷裂伸張率	<b>DIN53354</b>	<b>%</b>	經 Warp	<b>19.9</b>
			緯 Weft	<b>26.9</b>
<b>Tear Strength</b> 撕裂強度	<b>DIN53363</b>	<b>N</b>	經 Warp	<b>500.0</b>
			緯 Weft	<b>279.5</b>
<b>Adhesion of coating Strength</b> 剝離負荷	<b>DIN53357</b>	<b>N/3cm</b>	經 Warp	<b>53.87</b>
			緯 Weft	<b>94.17</b>
<b>Remarks</b> 備註				



This technical data is offered as helpful suggestion only.  
It's accurate to the best of our knowledge at time of printing.